

---


**Product Information : STARBRILL SC9410**


---

**Product Information**

STARBRILL SC9410 is a rapid drying acrylic urethane clear coating which is a 4: 1 clear coating with excellent appearance and gloss, with very fast drying, drying at 60 ° C in 9 minutes. Unlike other quick-drying type creel products, it is a general-purpose quick-dry type creel that can be multi-operation with slow touching drying compared to quick drying, and can be applied to partial coating and full painting. It has good spraying workability and excellent leveling ability and leveling property, so that the amount of paint can be reduced because the paint film is thick enough even with a small amount of paint.

Mixing Ratio	STARBRILL SC9410	(Volume ratio)
	STARBRILL SC9410 <A>	<A> 100
	SCH41 Standard<B> SCH42 Slow<B> SCH40 Fast<B>	<B> 25

**Specification**


STARBRILL SC9410 <A>  
SCH42/41/40 <B>  
Mixing ratio (volume ratio)  
100:25 (A:Thinner)



Drying Time  
Forced drying 60 ° C, 9 minutes  
Natural drying 20 ° C, 1-2 hours



Wear respirator or dust mask when working.



2~3Bar(Gravity spray gun)  
Number of paintings: 2 times  
Film Thickness 40~60 $\mu$ m  
Gun diameter: 1.2~1.5mm



3~4Bar(Suction type spray gun)  
Number of paintings: 2 times  
Film Thickness 40~60 $\mu$ m  
1.4~1.6mm

**Shelf time**

6 hours (25 ° C) when using standard hardener SCH41  
Please use within 6 hours after mixing.

**Spray viscosity** Ford Cup #4(25°C): 16~18sec